



SOLSATEX™2040

SOLSATEX™ 2040 is an anionic tapioca starch powder.

Requirements

Moisture content	Maximum 13 mg/g
Viscosity	20 ... 40 mpas
pH	6.5...7.5

Test methods

Moisture content	ISO 1666
Viscosity (in solution)	Concentration : 91 mg/g dry product in distilled water Total quantity : 1036 g (= 1000ml) Equipment : direct steam Cooking temp. : ~ 100 °C Cooking time : 20 minutes Shear : high speed mixing 3000 rpm for 1 minute Kottthoff Mischsirene
pH	Measuring temp : 85 °C Viscosity meter : Brookfield RVDV-II 20 rpm, spindle 1 The solution obtained from the viscosity test is measured at 85°C

Storage

Store inside, cool and dry, in sound and well closed bags.
Recommended storage time not longer than 1 year.